



# HMP MINERALS PVT LTD

Regd. Office: 111, Industrial Area, Sion (E), Mumbai-400 022, India

Tel: +91 22 24090124/127, Fax: +91 22 24072949, E-mail: hmp@vsnl.com, sales@hmpindia.com, www.hmpindia.com

## CHINA CLAY (KAOLIN) PG

Natural, easily dispersible, off white, China Clay Powder, processed from selected rocks of very high quality.

	REGULAR FINE (RF)	MICRO FINE (MF)
	240 MESH	400 MESH
<b>Chemical Composition (Typical)</b>		
• Al <sub>2</sub> O <sub>3</sub> (%)	37 ± 3	37 ± 3
• SiO <sub>2</sub> (%)	45 ± 5	45 ± 5
• Fe <sub>2</sub> O <sub>3</sub> (%)	1.5 ± 0.5	1.5 ± 0.5
• Loss on Ignition (%)	12 ± 2	12 ± 2
<b>Physical Characteristics (Typical)</b>		
• Specific Gravity	2.6 ± 0.5	2.6 ± 0.5
• Bulk Density (loose-gm/cc)	0.45 ± 0.02	0.50 ± 0.02
• Oil Absorption (ml / 100 gm)	40 ± 2	45 ± 2
• Moisture Content	≤ 5 %	≤ 5 %
• Residue on 37 μ Sieve(240 mesh)	≤ 0.5%	--
• Residue on 37 μ Sieve(400 mesh)	--	≤ 0.5%

- Material as per buyer's specification can also be made available.

Although the facts and suggestions in this publication are based on our own research and are believed reliable, we cannot assume any responsibility for performance or results obtained through the use of our products, herein described, nor do we accept any liability for loss or damages directly or indirectly caused by our products. The user is held to check the quality, safety and all other properties of our products prior to use. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a licence.